



KEACO LLC
1006 ASSEMBLY CIRCLE
SCHERTZ, TX 78154

TEL: (210) 651-6688
FAX: (210) 651-9020

TECHNICAL DATA SHEET

KEAPAK™ KP-50 HEAT ACTIVATED COVER TAPE

FOR POLYSTYRENE CARRIER TAPE

Description : A heat activated static dissipative Cover Tape made of polyester film. Designed for use with carrier tapes made of polystyrene or PVC.

Dimensions : KEAPAK™ Cover Tape comes wound onto 3" ID plastic cores, 300 and 500 meters in length, and is available in the following widths (denoted in mm): 5.3, 9.2, 13.3, 21.0, 21.3, 25.5, 37.5, 49.5, 65.5 and 81.5. Slitting tolerance for all widths is ± 0.1 mm. Custom widths and lengths are available upon request.

Recommended Sealing Conditions :

Temperature:	140° – 180° C
Sealing Time:	0.25 – 0.40 seconds
Shoe Width:	0.015 – 0.020 inches
Pressure:	30 – 40 psi

Designed to perform at various temperatures and dwell times within industry standards. 175°C, 0.1 second and 10 psi are suggested initial settings for heat, dwell, and pressure. For stronger adhesion, use a combination of higher temperature, longer dwell time and/or increased pressure.

Shelf Life : Best if used within eighteen months

Storage : Store at 70° F, ± 30°, (21°C, ± 17°C); Relative Humidity 50%, ± 30%

Properties	Value	Test Method
Electrical :		
Surface Resistivity :	<1 x 10 ¹¹ Ohms/square typical (both sides)	ASTM D-257
Strength :		
Break Strength :	20 lb. / inch width	ASTM D822A
Elongation at Break :	70% min.	ASTM D882A
Clarity :		
Haze :	40% max.	ASTM D1003

1/01/19

The information above is based on our experience to date and we believe it to be reliable. It is intended only as a guide for use at your discretion and risk. We assume no liability in connection with the use of the product described above. None of the information herein shall be taken as a license to operate under, or a recommendation to infringe, any patents. KEACO LLC makes no warranty, expressed or implied, as to the suitability of these materials for any specific use.